

IN THE CLAIMS

1. (Cancelled)
2. (Previously amended) The vacuum treatment chamber of claim 13, wherein $S \geq 1$.
3. (Previously amended) The vacuum treatment chamber of claim 13, wherein the slots have a width d , wherein $d \leq 2$ mm.
4. (Previously amended) The vacuum treatment chamber of claim 13, wherein the screen comprises metal and is connected with an electrical reference potential.
5. (Original) The vacuum treatment chamber of claim 2, wherein the slots, viewed from above and in an axial direction, are offset (φ) in relation to the radial direction (r).

6 -12. (Cancelled)

13. (Currently amended) A vacuum treatment chamber for workpieces comprising a treatment space, at least one induction coil encircling said treatment space having a coil axis at least for contributing to generation of a plasma within said treatment space, a self-contained hollow screen body having an inner surface and an outer surface, and arranged substantially coaxially to said coil axis [around] within said treatment space, said inner surface being freely exposed to said treatment space, said hollow screen body having a pattern of through-slots extending substantially in a direction of said coil axis and being distributed around said coil axis to allow for free line-of-sight paths from a

chamber wall to said coil axis, with a density S of said slots of said pattern per cm [of one of said inner and of said outer surfaces and] taken in [the] a circumferential direction of said [coil axis] screen body being at least 0.5.

14. (Previously added) The vacuum treatment chamber of claim 13, wherein said vacuum chamber further comprises a dielectric material chamber wall, and said at least one induction coil is mounted one of outside and of inside said chamber wall.

Sub
C1
B2
Cont'd
15. (Previously added) The vacuum treatment chamber of claim 13, further comprising at least two electrodes mutually distant from each other inside said treatment chamber and facing said treatment space, said at least two electrodes being operatively connected to an electric supply source selected from the group consisting of a DC source, and AC source, an AC+DC source, pulsed DC source, and an Rf-source so as to contribute to generating said plasma.

16. (Previously added) The vacuum treatment chamber of claim 13, further comprising a plasma density measuring apparatus and configured to output a signal indicative of instantaneously prevailing plasma density of said plasma, the output thereof being operatively connected as an actual value input of a negative feedback control circuit whose output is operatively connected to said at least one induction coil for adjusting said plasma density.

17. (Currently amended) The vacuum treatment chamber of claim [13] 16, wherein said plasma density measuring apparatus comprises a voltage

measuring apparatus having an input, operatively connected to an electrode arranged to be exposed to said plasma.

18. (Previously added) The vacuum treatment chamber of claim 16, wherein said plasma density measuring apparatus is mounted to one of a workpiece support and a target electrode within said vacuum treatment chamber.

Sub
C1
19. (Currently amended) A method for manufacturing vacuum surface treated workpieces, comprising:

evacuating a vacuum treatment chamber;

introducing a workpiece into a treatment space of said vacuum chamber;

generating in said treatment space a plasma, at least partially inductive with the use of a coil surrounding said treatment space;

providing a self-contained hollow screen body with an inner surface and with an outer surface coaxially to said coil, with said inner surface being freely exposed to said treatment space;

[providing in] said hollow screen body having a pattern of through-slots extending substantially in a direction of an axis of said coil and distributed around said coil axis to provide free line-of-sight paths from a chamber wall to said coil axis, a density S of said slots of said pattern per cm taken in a circumferential direction of said [coil axis] screen body being at least 0.5; and

surface-treating in said treatment space said workpiece exposed to said plasma.

20. (Previously added) The method of claim 19, further comprising generating during said surface-treating of said workpiece electrically conductive material freed into said treatment space.

21. (Previously added) The method of claim 19, further comprising providing said screen body of metal material:

22. (Currently amended) The method of claim 19, further comprising exchanging said screen body [upon] when said inner surface [having] thereof has been [loaded] saturated by said surface-treating of said workpiece to a predetermined extent.

23. (Previously added) The method of claim 19, wherein surface treating of said workpiece is one of sputter-etching and sputter-coating.

24. (Previously added) The method of claim 19, further comprising separating, by said screen body, said treatment space from a further space around said outer surface of said screen body, and feeding gas into said vacuum treatment chamber and thereby into said further space.

25. (Previously added) The method of claim 19, thereby selecting said density S to be ≥ 1 .

26. (Previously added) The method of claim 19, further selecting a width d of said through slots to be ≤ 2 mm.

27. (Previously added) The method of claim 19, further comprising operatively connecting said screen body electrically on a reference potential.

Sub
C1
BB
Cont'd

28. (Previously added) The method of claim 19, further comprising additionally generating said plasma by at least two electrodes exposed to said treatment space capacitively, thereby feeding said at least two electrodes by one of DC, AC, AC+DC, pulsed DC and Rf.

29. (Previously added) The method of claim 19, further comprising monitoring an actual value of density of said plasma and negative-feedback controlling said density by adjusting an induction field generated by said coil within said plasma.

30. (New) The vacuum treatment chamber of claim 13, whereby said density S is selected to be ≥ 1 .

Sub
C1
BB
Cont'd

31. (New) The vacuum treatment chamber of claim 13, further selecting a width d of said through-slots to be ≤ 2 mm.

32. (New) The vacuum treatment chamber of claim 13, further selecting a width d of said through-slots to be ≤ 1 mm.

33. (New) The vacuum treatment chamber of claim 13, wherein said screen body is operatively electrically connected on a reference potential.

34. (New) The vacuum treatment chamber of claim 13, wherein the maximum width of the slots is 2 mm.

35. (New) The method of claim 19, wherein the coil is operated at a frequency f_m of $100 \text{ kHz} \leq f_m \leq 800 \text{ kHz}$.

36. (New) The method of claim 19, wherein the coil is operated with a frequency f_m of about 400 kHz.